

Keratherm – MT 103

Flexible ceramic heat conducting and isolating tape



Thermoplastic elastomer tape with very good isolating behavior, excellent mechanical properties and good thermal characteristics

DISCLAIMER: Purchaser shall be solely responsible for determining the adequacy of the product for any and all uses which the purchaser shall apply the product, and the application of the product by the purchaser shall not be subject to any implied warranty of fitness for that purpose.

Properties	symbol	unit	MT 103
Color			Red
Thermal Properties			
Thermal Resistance	R_{th}	K/W	0.31
Thermal Impedance	R_{ti}	$^{\circ}\text{Cmm}^2/\text{W}$	124
		Kin^2/W	0.17
Thermal Conductivity	λ	W/mK	1.8
Electrical Properties			
Breakdown Voltage	$U_{d,ac}$	KV	10
Volume Resistivity		Ωcm	4.7×10^{10}
Dielectric Loss Factor (1khz)	$\tan \delta$	1	1.0×10^{-3}
Dielectric Constant (1khz)	ϵ_r	1	2.61
Mechanical Properties			
Thickness ($\pm 10\%$)		mm	0.225
Hardness		Shore A	60
Tensile Strength		N/mm^2	2
Elongation		%	> 200
Physical Properties			
Application Temperature		$^{\circ}\text{C}$	-40 to +125
Flameclass		UL 94	being tested

The following thicknesses are available:

0.2 mm, 0.25 mm, 0.3 mm, 0.4 mm, 0.5 mm

Advantages of MT 103

- Very good price/performance ratio
- Very good mechanical properties
- Very good insulating properties
- Silicone free

Delivery forms:

- 1.) Bulk good
- 2.) Optional with single sided adhesive coating
- 3.) Already punched geometries

Compressibilities of Keratherm® of MT-Film

