

GFL 3020



- Two component silicone
- Room temperature curing
- Suitable for wet in wet production

Applications

- Applications with high tolerances
- Encapsulation
- Electrical vehicles
- High energy rechargeable batteries

Options

- Available in syringes for small applications and cans for dispensing solutions

| Properties | Unit | GFL 3020 |
|----------------------------------|-------------------|---------------------------|
| Color | | Yellow |
| Mixing Ratio | | 1 : 1 |
| Curing Time | h | 1 (at RT) |
| Thermal Properties | | |
| Thermal Conductivity | W/mK | 1.8 |
| Thermal Resistance | K/W | 0.7 |
| Electrical Properties | | |
| Breakdown Voltage $U_{d; ac}$ | kV | 10 |
| Dielectric Breakdown $E_{d; ac}$ | kV/mm | 20 |
| Mechanical Properties | | |
| Hardness | Shore 00 | 45-60 |
| Physical Properties | | |
| Application Temperature | °C (°F) | -40 to +200 (-40 to +392) |
| Density | g/cm ³ | 2.3 |
| Viscosity | Pas | 45-70 |
| Total Mass Loss | Ma. % | 0.19 |
| Flame Rating | UL-94 | V-0 |
| Possible Thickness | mm (inch) | 0.2 to 5.0 (0.008 to 0.2) |

The data provide engineering guidance, performance in actual applications should be established through testing.