

## GFL 3025



- Two component silicone
- Room temperature curing
- Suitable for wet in wet production

### Applications

- Applications with high tolerances
- Encapsulation
- Electrical vehicles
- High energy rechargeable batteries

### Options

- Available in syringes for small applications and cans for dispensing solutions

Properties	Unit	GFL 3025
Color		Orange
Mixing Ratio		1 : 1
Curing Time	h	1 (at RT)
<b>Thermal Properties</b>		
Thermal Conductivity	W/mK	2.5
Thermal Resistance	K/W	0.5
<b>Electrical Properties</b>		
Breakdown Voltage $U_{d; ac}$	kV	8
Dielectric Breakdown $E_{d; ac}$	kV/mm	16
<b>Mechanical Properties</b>		
Hardness	Shore 00	65-85
<b>Physical Properties</b>		
Application Temperature	°C (°F)	-40 to +200 (-40 to +392)
Density	g/cm <sup>3</sup>	2.83
Viscosity	Pas	45-75
Total Mass Loss	Ma. %	<0.09
Flame Rating	UL-94	V-0
Possible Thickness	mm (inch)	0.2 to 5.0 (0.008 to 0.2)

The data provide engineering guidance, performance in actual applications should be established through testing.